Small band gap copolymers based on furan and diketopyrrolopyrrole for field-effect transistors and photovoltaic cells

Bijleveld, Johan C.; Karsten, Bram P.; Mathijssen, Simon G.J.; Wienk, Martijn M.; Leeuw, Dago M. de; Janssen, René A.J.

Published in:
Journal of Materials Chemistry

DOI:
10.1039/c0jm03137b

Publication date:
2011

Electronic Supporting Information

Small band gap copolymers based on furan and diketopyrrolopyrrole for field-effect transistors and photovoltaic cells

Johan C. Bijleveld,[a] Bram P. Karsten,[a] Simon G. J. Mathijssen,[ab] Martijn M. Wienk,[a] Dago M. de Leeuw,[b] and René A. J. Janssen*[a]

Table S1. Onset of UV-vis absorption of the DPP-XYX polymers in oDCB and $CHCl_3$ solution at different temperatures.

	oDCB	$CHCl_3$	
	20 °C	20 °C	60 °C
Polymer	$E_{g,}$ (eV)	E_g (eV)	E_g (eV)
FPF	1.52	1.52	1.55
TPT	*a*	1.56	1.58
FFF	1.43	1.47	1.50
FTF	1.45	1.46	1.48
TFT	1.43	1.44	1.47
TTT low M_n	1.39	1.38	1.43
TTT high M_n	1.37	1.35	1.36

[a] Not soluble

[a] *Molecular Materials and Nanosystems, Eindhoven University of Technology, PO Box 513, 5600 MB Eindhoven, The Netherlands. E-mail: r.a.j.janssen@tue.nl.*

[b] *Philips Research Laboratories, High Tech Campus 4, 5656 AE Eindhoven, The Netherlands.*



Figure S1. Variable temperature UV-vis-nearIR absorption spectra recorded in $CHCl_3$ solution between 20 and 60 °C for the six DPP-XYX polymers.



Figure S2. *p*-Type transfer curves of FETs made with the four furan based DPP-XYX polymers. Drain current is normalized with respect to the channel length for direct comparison.



Figure S3. *n*-Type transfer curves of FETs made with the four furan based DPP-XYX polymers. Drain current is normalized with respect to the channel length for direct comparison.